TECHNICAL DATA SHEET



DIAMETED



DIAIVIETEN	♥ 3.1		
SHANK	• Ring		
FINISHES	• Stainless Steel		
COLLATION	Paper laminated strip nails		
T00LS	• PSN90 - PSN100 - PF90 IM350 - IM90i - IM100i		

MATERIAL PROPERTIES / DIMENSIONS

• 2 1

- Tensile strength wire: minimum 700 N/mm²
- Diameter, Shank (Ds)1: 3.10 mm
- Diameter, Profile minimum (Dp): 3.20 mm
- Diameter, Head (Dh) / (Dh)¹ / (Dh)²: 6.50 / 7.60 / 5.30 mm
- Nail length total (Lt)1: 80 / 90 mm

INTENDED USE - CORROSION PROTECTION

Timber-to-Timber




Finishes	Eurocode 5 Service Class	Label colour on packaging
	Service Class 1 Indoor use	
Stainless Steel A2 - AISI 304	Service Class 2 Outdoor protected use	Yellow
	Service Class 3 Outdoor use	

NAIL DIMENSIONS*

Ds (in mm)	Length Lt (in mm)	Lring min. (in mm)	Lp max. (in mm)	
3.1	80	57.9	4.7	
3.1	90	65.9	4.7	

* In order to select the correct nail length for a given connection please always consult standards and good practice on your local market.

No. 3.4.2/53 EN 14592







36 nails per strip

40 nails per strip

CHARACTERISTIC PARAMETERS

"Calculated or tested according to EUROCODE 5"

Head pull-through	Withdrawal	Yield moment
f _{head,k} [N/mm²]	f _{ax,k} [N/mm²]	M _{y,k} [Nmm]
20.72	10.11	3 257
1		45° max.

- Values are based on a mean characteristic wood density of 350 kg/m³.
- · Characteristic parameters must always be reduced to design values by using partial factors.

¹ Tolerance according to EN10218-2 for wire diameter and according to EN14592 for the nail length.

² Tolerance ± 0.3 mm.

³ Please check availability of the reference in the Product Catalogue.