

LION oil tempered



LION Oil tempered hardboard is impregnated with special oil which is polymerised by heat treatment during the manufacturing process.

This treatment gives the board increased moisture resistance properties and higher bending strength values. Typical end uses include internal wall or roof linings, signs, fascias and flooring underlay.

Technical properties

Thickness [mm]	3 / 4,8 / 6
Standard sizes [mm]	1220 x 1830/2440/2745/3050
Density [kg/m³]	1000
Bending strength [N/mm ²]	3035
Internal bond [N/mm²]	0,30,6
Internal bond after boil te	st 0,250,3
Swelling in thickness (24 h	2025

Dimensional tolerances ± 2.0 mm/m, max ± 5 mm Width/length ± 1 mm cut to size Squareness ± 2.0 mm/m Edge straightness ± 1.5 mm/m Moisture content ± 4.9 %



Finnish Fibreboard Ltd.
Tel. +358 20 110 3300 • Fax +358 3 714 3700
www.finnishfibreboard.com